



YAPP, YAPP-M – used in the manufacture of rubber. YAPP, YAPP-M softeners are obtained by compounding the filtrate and ceresin fraction above 490 °C.

Typical physical and chemical properties

Parameter	Method	Values	
		YAPP	YAPP-M
Melting temperature, °C	p. 3.2 GOST 23683-89	63	57
Total acid number, mg KOH/g on 1 g softener	GOST 5985-79	Absence	
The content of water soluble acids and alkalis	GOST 6307-75	Absence	
Mechanical impurities content, %	GOST 6370-83	0,01	
Water content , %	GOST 2477	vestige	
Mass fraction of sulfur, %, no more	ASTM D 4294-03	0,1	